

Rate of Paper Degradation
The Predictive Value
of Artificial Aging Tests

Henk J. Porck

European Commission
on Preservation and Access, Amsterdam

2000

*The European Commission on Preservation and
Access gratefully acknowledges the financial support
of the following institutions and organizations*

Bayerische Staatsbibliothek

Biblioteca Nacional de España

Biblioteca Nacional de Portugal

British Library

Direction des Archives de France

General State Archives of the Netherlands

Koninklijke Bibliotheek, the national library of the Netherlands

Liechtensteinisches Landesarchiv

Liechtensteinische Landesbibliothek

National Archives of Finland

National Archives of Hungary

National Archives of Ireland

National Archives of Norway

National Archives of Scotland

National Archives of Sweden

National Library of Finland

National Library of Scotland

National Library of Wales

National Széchényi Library, Hungary

National and University Library of Iceland

Public Record Office, the National Archives of England, Wales and
the United Kingdom

Royal Library of Sweden

Royal Netherlands Academy of Arts and Sciences

Swiss Federal Archives

About the Autor

Henk J. Porck (1953) studied biochemistry at the Free University (VU) of Amsterdam. His Ph.D. thesis was a biochemical-genetic study at the VU Medical Faculty Department of Anthropogenetics. In 1983 he was appointed conservation scientist at the Koninklijke Bibliotheek (KB), the National Library of the Netherlands in The Hague. Research projects in paper conservation include studies on deacidification, artificial aging, ink corrosion and discoloration. In 1991 he also took up the curatorship of the KB Paperhistorical Collection. In the field of paper historical research, his work has concentrated on the analysis of contemporary, 19th- century studies on the quality of Dutch paper, and on the classification and identification of 18th- and 19th- century decorated papers.

Reactions on this report can be sent to:

Dr. H.J. Porck, Conservation scientist

Department of Research and Network Services

Koninklijke Bibliotheek, National Library of the Netherlands

P.O. Box 90407

2509 LK The Hague

The Netherlands

henk.porck@kb.nl

Contents

Preface 7

Summary 9

Introduction 11

 Background 11

 Questions 11

 Objectives and set-up 11

Theory and Practice 13

 Principles and techniques of artificial aging 13

 Methods and applications 14

 Natural and artificial aging 19

Discussion 25

 Evaluation 25

 Conclusions 27

 Recommendations 27

References 29

Preface

This publication is a translation of the Dutch report *Snelheid van papiervervalde betrouwbaarheid van prognoses op basis van kunstmatige-verouderingstests* (Porck 1999), resulting from a desk research project of the Koninklijke Bibliotheek (KB). The study was subsidized by the Ministry of Education, Culture and Science of The Netherlands, in the framework of *Metamorfoze*, the Dutch National Program for the Conservation of Library Materials. As a consequence of additional reviewing of the translated version, some corrections have been made in the original text.

In the preparation of this report, W.J.Th. Smit (Department of Conservation and Optical Technics, KB) offered valuable support. Useful contributions and comments were also made by H.J. Jansen and S. Pauk (Department of Research and Network Services, KB), and C.B.J. de Wolf (Collection & Research Division, KB).

Dr. D. Erhardt (Smithsonian Center for Materials Research and Education, Suitland, MD), Dr. H. Bansa (Bayerische Staatsbibliothek, München), Dr. J.C.M. van Eijndhoven (Rathenau Institute, The Hague), Dr. J. Down (Canadian Conservation Institute, Ottawa), Dr. V.D. Daniels (British Museum Conservation Department, London) and Dr. R.L. Feller (former co-worker Carnegie Mellon Research Institute, Pittsburgh) are acknowledged for their contributions to the discussion and worthwhile suggestions.

Dr. J.B.G.A. Havermans (TNO Paper & Board Research, Delft), Dr. N.S. Baer (Fine Arts Institute, New York University), Dr. E. McCrady (Abbey Publications, Austin, TX) and Y. de Lusenet (ECPA, Amsterdam) critically reviewed the manuscript and offered many useful comments and recommendations.

Henk Porck

Summary

During artificial or accelerated aging a material is subjected to extreme conditions in a climate-chamber to try to speed up the natural aging process. Artificial aging tests are often used to determine the permanence of paper, i.e. its rate of degradation, as well as to predict the long-term effect of a conservation treatment. However, there are still many questions surrounding the actual predictive value of these tests. The present report, based on specialist literature and discussions with experts, aims at providing an overview of the current state of affairs concerning the possibilities and limitations of artificial aging analysis. The report is not only intended for conservation scientists involved in research in this field, but also for those responsible for the development of a conservation policy.

Since the fifties a great variety of artificial aging methods has been developed for paper, and the field of application of these methods in the practice of conservation of archival and library materials has broadened enormously. Nevertheless, fundamental and experimental research into the reliability of artificial aging analyses is only performed on a limited scale. An evaluation of this research indicates that the essential questions have not been resolved satisfactorily, and that findings have not resulted in the use of a generally accepted standard method. Differences in opinion still prevail, and there are evident disagreements with respect to the conditions under which artificial aging should preferably be performed.

In this report it is shown that the results of artificial aging tests currently available do not allow for a reliable determination of the rate of paper degradation in absolute terms. Meaningful application of the tests is limited to qualitative, relative statements on the expected effects of conservation treatments and on the role of the various reactions that contribute to the deterioration of paper.

The present report offers several practical recommendations and suggestions on alternative approaches to the question of how quickly paper deteriorates. It is also proposed to organize a meeting on this topic, for instance under the auspices of the ECPA or the CLIR. Such a meeting should help to break through the present deadlock characterized by uncertainty and doubt, and work out an agenda for a joint approach to the problem.

Introduction

Background

In conservation research methods are often being used that aim to accelerate the natural degradation of archival and library materials. In this way, scientists try to obtain more insight into the permanence of certain materials, the long-term effects of conservation treatments and the mechanisms of specific deterioration processes.

For these artificial or accelerated aging methods, a material is exposed in a climate-chamber to extreme conditions in terms of temperature and humidity for a certain period of time, during which the changes occurring in the material are measured. Subsequently, from the data obtained in this way, the rate at which the material in question will deteriorate under normal, natural conditions of storage is deduced. By comparison of the findings with untreated reference material, it is attempted to determine the expected effect of a certain conservation treatment. In addition, artificial aging tests can be used in order to study, or simulate, the physicochemical reactions of the natural aging process.

Questions

Although artificial aging tests have been used as a general research tool in the past decades, several serious questions with regard to the actual predictive value of these tests still exist. Both in the current specialist literature and in the more informal discussions in the conservation science community, the use of artificial aging, especially with regard to paper, is a subject of debate. The following are some of the questions that are being discussed:

1. Are the present (standard) methods for artificial aging, which in first instance have been developed for modern papers, suitable to study papers which have already undergone a natural and, depending on the storage conditions, also variable process of natural aging?
2. Are artificial aging tests meaningful for the determination of the actual rate of natural paper degradation, and thus suitable for making reliable predictions?
3. Can artificial aging analysis be used for the determination of the quantitative effect of a conservation treatment, or is the application of the results of this analysis limited to qualitative, relative interpretations?
4. To what extent are the reaction mechanisms of paper degradation which occur in artificial aging, equivalent to those under normal, natural storage conditions?

Objectives and set-up

The lack of consensus on the questions above presents a serious problem, both from a fundamental scientific point of view as for the practice of conservation. In order to motivate and plan conservation activities, and to reserve the necessary funds, it is important to have an accurate indication of the rate of paper decay, as well as a reliable insight into the medium- and long-term effect of a certain conservation treatment or measure.

For these reasons, the Koninklijke Bibliotheek has taken the initiative to address this issue, within the framework of the research activities of the national conservation program *Metamorfoze*. In planning the project, it was envisaged that the results should be useful for scientists directly involved in conservation research, as well as policy-makers in the field of preservation of archival and library materials.

The goal of the present report is to provide an up-to-date overview of the research and scientific debate on the theoretical basis and practical use of artificial aging. The final section of the report is devoted to a critical evaluation of the possibilities and limitations in the determination of the rate of paper degradation and other applications of artificial aging tests. Finally, several conclusions are drawn and some recommendations for the future formulated.

This study is also intended as a discussion paper for the committee on artificial aging of the working group 'Archive and Library Conservation', established by the Netherlands Institute for Cultural Heritage (NICH) in Amsterdam for the exchange and dissemination of knowledge and practical experience between conservators and conservation scientists.

Besides relevant specialist literature, the possibilities of the 'electronic highway' have also been explored in this project. By means of several issues of an 'aging newsletter', distributed by e-mail, it was tried to poll the opinions of a number of experts in the Netherlands and abroad. Both the literature and the discussion on Internet, which unfortunately only received limited response, clearly brought to light the current uncertainty and many points of disagreement.

Theory and practice

Principles and techniques of artificial aging

Just like all other organic materials in archives and libraries, paper is subjected to a number of fundamental deterioration processes. Under normal conditions of storage, these processes are very slow, but eventually and inevitably they still lead to well-known aging effects such as yellowing and loss of strength.

The most common reaction is the hydrolytic degradation of the cellulose molecules, the building blocks of paper, in which the presence of water (moisture) plays an essential role. According to standard reaction-kinetic principles, the rate of the hydrolytic process is determined by the temperature, the acidity (pH value), and the amount of moisture present in the paper. The moisture content is again dependent on the (relative) humidity in the storage environment.

The second deterioration process is the oxidative degradation of cellulose, primarily induced by the presence of oxygen in the environmental air. The third main mechanism of deterioration is the process of thermal degradation. This mechanism concerns the breakage of chemical bonds as a consequence of the temperature-dependent movements of the cellulose molecules and their constituent atoms.

Arrhenius-tests

The three deterioration reactions mentioned above take place simultaneously in the natural aging process of paper. Although the individual rates of these reactions vary, it is assumed that the overall rate of the degradation process is systematically related to the temperature, provided that the other environmental conditions are constant. Therefore, it appears possible to use the results of artificial aging at high temperatures to deduce the rate at which the deterioration process will take place at cooler, *casu quo* normal storage conditions.

The argument for the use of elevated temperatures in artificial aging relies on the fact that in general a reaction proceeds faster at higher temperatures, which makes it possible to observe its effects, in this case the loss of paper strength, more quickly than at room temperature. Such artificial aging experiments are sometimes called 'Arrhenius-tests'. In these tests, performed at different temperatures and a constant relative humidity of the environment (in a climate-chamber), a characteristic property of the paper, such as folding endurance or tear resistance, is measured at regular time intervals. By determining how many days of artificial aging (d) are needed at different aging temperatures (T) to obtain a certain measure of paper degradation (for instance a certain percentage of loss in folding endurance), a temperature-versus-'time needed' graphics can be made, i.e. an Arrhenius-plot. When the factor 'time' is plotted in a logarithmic scale ($\log d$), and the temperature in a reciprocal scale ($1/T$), the Arrhenius-plot will theoretically show a straight line, reflecting a proportional relationship. By simply lengthening (extrapolating) this straight line to lower temperatures – that is below the temperatures at which the artificial aging was performed – it can be seen from the

Arrhenius-plot how much time would be needed for the same level of paper decay to occur at normal storage temperature. This procedure allows, in theory, the prediction of the rate of paper degradation at any temperature, thus also for instance at storage conditions below room temperature (cool storage).

Other uses

Except for the Arrhenius-test, the principle of the acceleration of chemical reactions is especially applied to predict the long-term effects of conservation treatments. In this case, the primary focus is not on the quantification of the influence of the treatment on paper permanence, but on the comparison of the effect of artificial aging between treated papers and untreated reference papers. On the basis of this comparison it is subsequently concluded whether or not the conservation treatment offers a significant benefit with regard to the aging resistance of the paper. For this purpose, instead of different high temperatures and measurements at regular intervals, fixed (standardized) aging conditions are used. The analyses of paper properties are often limited to one measurement before and one after the aging test. The examples of such tests presented in the next section will show that, in addition to the elevation of the temperature, other 'stimulating' conditions are applied in order to speed up the deterioration processes.

Finally, the acceleration of deterioration reactions is used to simulate certain types of damage in order to study the fundamental mechanism of the degradation. This approach enables the investigation of the relation between the visual appearance of the damage and the underlying deterioration reactions. In addition, simulating a specific type of damage under laboratory conditions offers a suitable alternative for the use of original collection materials in the development of conservation methods.

Methods and applications

The literature in the field of conservation research shows a great variety of artificial aging tests (Neimo 1964; Pravilova 1964; Rahn 1974; Brown 1991). In the first place, the objectives and as a consequence the ways of performance of these test strongly differ (Feller 1994a). Though not often indicated explicitly in the research reports, the three procedures mentioned above – Arrhenius-tests, comparative studies and simulation experiments – can be distinguished. Within these three groups a further subdivision is possible into different concrete applications.

In the second place, there are many differences in the actual methods themselves: the conditions under which the artificial aging is performed in the climate-chambers, which are sometimes constructed especially for these purposes. Among these methods are several international and national standards, such as:

- ISO-standards from the International Standards Organization (ISO 1982, 1985, 1986a,b);
- TAPPI-standards from the Technical Association of the Pulp & Paper Industry (TAPPI 1963, 1985a,b);

- ASTM-standards from the American Society for Testing and Materials (ASTM 1971, 1987);
- NEN-standards from the Netherlands Normalization Institute (NEN 1983);
- CSN- and AFNOR NFQ-standards from normalization institutes in respectively the Czech Republic and France (Hanus 1987, 1995, 1996; Daniel 1992).

In spite of the availability of these standards, other methods, often developed individually by research institutes, are used much more frequently in practice.

It should be pointed out here that the methods of artificial aging used in paper conservation are as a rule deduced from procedures developed in the paper industry for research on and production of special materials, such as heat- and fire-resistant types of paper and board (Back 1963, 1967a,b; Wink 1968; Fung 1969).

In the following table, a chronological overview is presented of a number of concrete and illustrative examples of artificial aging methods with their respective fields of application, selected from the specialist literature of the last decades. The descriptions list, in consecutive order, temperature (°C), relative humidity (RH in %), presence of other 'stimuli' (lighting, radiation, presence of gases such as oxygen [O₂], sulfur dioxide [SO₂], nitrogen oxides [NO_x], nitrogen dioxide [NO₂]), and if indicated, the duration of the aging treatment in days (d) or hours. If several aging methods have been used in combination, they are presented separated by a semicolon (;).

Additional notes: the notation 100/150 means: 100 or 150; 100-150 means: different values ranging from 100 to 150. If data on relative humidity (RH) are not given, it has to be taken into account that at high temperatures (>90 °C) climate chambers are comparable to ventilated ovens, and under these circumstances an RH value of 1-5% usually prevails.

| method | application | reference |
|---|---|--------------------------|
| 20°C, SO ₂ treatment, 7d | influence of air pollutants | Langwell 1955 |
| 80°C, 70%RH, 5-30d | effect of paper strengthening with polymethyl acrylate | Yabrova 1958b |
| 70°C, 50%RH, 10d; 100°C, 0/50%RH, 3d | permanence of different sorts of paper | Fink 1965 |
| 90°C, 0/50%RH, O ₂ treatment, 1-24d | mechanism of aging, role of oxygen | Parks 1971a, 1971b, 1972 |
| 105-150°C, 0%RH, O ₂ treatment, <1d | mechanism of aging role of oxygen | Medved 1973 |
| 90°C, 13d; 35°C, lighting, 12d; 90°C, radioactive radiation | effect (self) adhesive tapes | Skall 1974 |
| 100°C, 0/100%RH, O ₂ treatment, 1-10d | role of oxygen and moisture in aging | Arney 1979 |
| 90°C, 50/100%RH, 7-35d | influence of washing with water | Tang 1979 |
| 60-120°C, 100%RH, O ₂ treatment, 1-10d | role of oxygen and temperature in aging | Arney 1980 |
| 90°C, 100%RH, O ₂ treatment and various pH-values, 1-28d | role of oxygen and acidity [pH] in aging | Arney 1981 |
| 90°C, 50%RH, 7-21d | production test material, influence RH on folding endurance | Sclawy 1981 |
| 70-100°C, 2/50%RH, 3-179d | mechanism of aging | Mendenhall 1981 |
| 60-165°C; lighting and SO ₂ treatment | mechanism of copper corrosion | Banik 1982 |
| 100°C, 7d | influence of cleaning with eraser powder | Pearlstein 1982 |
| 103°C, 3-24d | mechanism of aging | Hanus 1987 |
| 80°C, 10-81d, paper samples in sealed glass tubes | influence historical papermaking techniques | Barrett 1989 |
| 80°C, 65%RH, 12d | permanence of paper types | Ernst 1989 |
| 90°C, 40/60%RH (change in RH every 12 hours), 1-32d | influence of fluctuating storage conditions | Shahani 1989 |
| 90°C, lighting, 3-30d | effect cellulose ethers on discoloration | Feller 1990 |
| 90°C, 56%RH, 16d | effect cellulose ethers on folding endurance and acidity | Baker 1991 |
| 70°C, 0%RH, 35/42d; treatment with exhaust-fumes | influence of gelatin-sizing | Barrett 1992 |

Artificial Aging Methods and Applications (continued 1)

| method | application | reference |
|---|---|--------------------------------|
| 80°C, 65%RH, 12d; 30°C,50%RH,lighting,ca.6d | influence of optical whiteners | Flieder 1992; Leclerc 1993a |
| 90°C,60%RH,7d;28°C,80%RH, SO ₂ and NO ₂ treatment,7d | effect mass deacidification, effect air pollution on deacidified paper | Daniel 1992 |
| 105°C, 3d | influence of storage in inert gas (argon) | Havermans 1992 |
| 90°C, 50%RH, 28d | production of test material, effect conservation of transparent-paper | Hofmann 1992; Reyden 1992 |
| 80°C, 60%RH, 7-28d; gamma radiation | simulation of degradation, production of paper for conservation purposes | Inaba 1992 |
| 90°C, 55%RH, 40d | production of test material for non-destructive analysis | Priest 1992 |
| 90°C, 50%RH, 20d | influence of bleaching by means of moisture and light | Schaeffer 1992 |
| 80°C,95%RH,1-32d;22°C,65% RH, SO ₂ and NO _x , 1-28d | effect mass deacidification, effect air pollution on deacidified paper | Banik 1993 |
| 50°C, 65%RH, 10d; 30°C, 50%RH,lighting,ca.12d | permanence of photocopies | Leclerc 1993b |
| 90°C, 65%RH, 30d; 30°C, 50%RH,lighting,ca.12d | stability of printing inks | Maraval 1993 |
| 90/50°C,80/35%RH(change in T,RH every 6 hours), 6d | effect of encapsulation in polyester film | Pauk 1993 |
| 60/100°C, 1-100d | effect of washing with water on gum arabic as binding agent | Daniels 1993 |
| 50-90°C, 30-38%RH, 2-1372d | mechanism of discoloration, role of temperature and RH | Vitale 1993 |
| 80°C, 65%RH, 6-24d | NEN-2728 and DIN-6738 standards for permanent paper | Berkhout 1994 |
| 90°C,50%RH,12d;23°C, 50%RH, SO ₂ and NO ₂ , 4d | effect mass deacidification, effect air pollution on deacidified paper | Havermans 1994,1995 |
| 105°C, 3-24d; | effect of disinfection with ethylene | Hofenk 1994 |
| 80°C, 65%RH, 3-24d | oxide and gamma radiation | |
| 80°C, 50%RH, 14-99d | production test material, effect mass deacidification | Kaminska 1994 |
| 90°C, 50%RH, 12d | effect mass deacidification with Battelle and DEZ system | Pauk 1994 |
| 103°C, 24d | influence of storage in boxes | Hanus 1995,1996 |
| 90°C, 50%RH, 12d | effect mass deacidification with Bookkeeper system | Pauk 1996a |

Artificial Aging Methods and Applications (continued 2)

| method | application | reference |
|--|--|------------------|
| 90°C, 50%RH, ca. 21d | effect of various strengthening methods | Bansa 1997 |
| 80°C,65%RH, 6-24d | influence of paper composition and production technique | Letnar 1997 |
| 90°C, 35/80%RH (change in RH every 3 hours) | simulation ink corrosion, effect of treatment methods | Neevel 1997 |

Natural and artificial aging

The application of artificial aging is assumed to be justified. However, this hypothesis must be verified in practice. This verification offers in addition the possibility to make adjustments to the artificial aging test used. In this way the relevance of the test in predicting the natural aging process can be optimized. On the basis of the literature and discussion with experts, an overview of the developments and current state of affairs will be presented below.

At the end of the nineteenth century the possibility to intensify the natural deterioration of paper artificially by dry heat treatment was already described (Herzberg 1899). In 1926 the Swedish Government Testing Institute compared the permanence of different papers after exposure to elevated temperatures and sunlight (Hall 1926). At the end of the twenties, research of the National Bureau of Standards (USA) showed that dry air at 100 °C resulted in the strongest and best reproducible aging effects. This finding formed the basis of the artificial aging method of 72 hours at 100 °C (Rasch 1929) which was often used since then. Later empirical studies, for instance by Wilson et al. (1955) and Barrow (1963), suggested that this artificial aging corresponds with 18-25 years of natural aging at room temperature. The applicability of a dry, thermal artificial aging test for the prediction of paper permanence was also confirmed in other studies dating from the fifties and sixties (Royen 1958; Barrow 1964).

Only a few investigations have been performed into other possibilities to stimulate natural aging (Kantrowitz 1940; Launer 1943). This may indicate that the heat treatment was generally accepted as a valuable method. In this context it is interesting to note that in the current research program of the American Society for Testing and Materials (ASTM) the focus will be on 'alternative' means in the development of artificial aging tests, aiming at the use of lighting and air pollutants (Arnold 1996).

In the course of the fifties it became increasingly clear that the tests so far performed by means of dry heat do not take into account the fact that aging under laboratory conditions fundamentally differs from the natural aging process taking place at normal relative humidities. For this reason the suspicion grew that these tests could well lead to the wrong conclusions (Richter 1956; Yabrova 1958a; Graminski 1970,1979; Wilson 1971; Arney 1979). In addition, gradually more doubts arose on the usefulness of artificial aging performed at only one raised value of the temperature. It was acknowledged that the reactions responsible for paper deterioration need not all be related to temperature in the same way, partly because of differences in activation energy, i.e. the minimal energy required for a reaction to take place (Stamm 1956; Royen 1957; Browning 1968,1969; Gray 1969,1977; Smith 1970; Graminski 1979; Arney 1980; Bansa 1984).

In first instance, these questions led to the conviction that an approach according to the Arrhenius-principles -artificial aging at one, more realistic value of relative humidity and at different temperatures, and extrapolation of the findings to room temperature- would be more justified from a scientific point of view (Baer 1974; Lindström 1989). However, there is still disagreement about the most suitable values for temperature and relative humidity. As a consequence, the variation in the conditions used for artificial aging is enormous. In a literature overview from 1964 the following ranges

are given: temperatures between 22 and 160 °C, relative humidities from 1% to 100%, and a duration of treatment between one hour and 180 days (Neimo 1964).

Problems

Nowadays the issue of temperature and relative humidity in artificial aging is still topical. It is worth mentioning that the well-known 'rule of thumb' that a rise in temperature of 10 °C results in a doubling of the reaction rate is considered not to apply to the deterioration process of paper (Erhardt 1989). In addition, arguments have been put forward that the absolute quantity of moisture in the air rather than the relative humidity is the factor determining the rate of deterioration (Bansa 1998b; Down 1998).

Moreover, there is another fundamental problem: while the field of application of the Arrhenius-principles concerns the reaction-kinetics of chemical transformations, the complex properties of paper which are often registered in artificial aging, such as folding endurance, tear resistance and paper discoloration, cannot actually be simply and unambiguously related to the chemical composition of the paper in question. Nonetheless, there are indications that under certain conditions the rate at which such characteristics change still exhibits a systematical relation to the chemical processes which are taking place during artificial aging. Therefore in practice, in the analysis of artificial aging, it is assumed that the principles of chemical reaction-kinetics do indeed apply (Luner 1969; Lindström 1989; Zou 1996; Erhardt 1998).

Complexity of the material

That there are still a number of snags in the application of artificial aging tests is also attributed in the literature to the complexity of the material itself. In the case of paper, we are not only dealing with cellulose containing vegetable fibers, but often with other compounds as well, such as lignin, fillers, pigments and sizing agents. As a consequence, paper should be considered as a multi-component system rather than as a singular substance, which complicates interpretation of the results of an artificial aging test (Baer 1977; Down 1998).

Another complicating factor concerns the way in which the paper is exposed to the aging conditions. Research findings from the Library of Congress (Shahani 1989, 1991, 1993, 1994), the Netherlands Institute for Cultural Heritage (Roelofs 1994), the Koninklijke Bibliotheek (Pauk 1996b) and the Australian National Library (Brandis 1997) have clearly indicated that paper in stacks, c.q. books, shows a different aging behavior compared to single, loose sheets. Some of these studies have shown that both under artificial and natural aging conditions, deterioration is more severe at the center of a stack of paper than at the regions more to the outside. In addition, damage surveys performed in several library collections had already demonstrated that in areas with relatively low air pollution, paper in book blocks can be significantly more acid (showing a lower pH value) in the middle of the pages than in the margins (Smith 1972; Porck 1990). This also points to a stronger aging process in the center of paper stacks than in the outer parts. This 'stack-versus-single sheet' phenomenon in the aging of paper is considered of major importance and will be studied in more detail in the future (Down 1998).

Comparison of artificial and natural aging

Only few investigations have been performed in which artificial and natural paper aging are directly compared (Wilson 1955, 1980; Royen 1957, 1958). In 1928 the National Bureau of Standards tested various chemical and physicochemical properties of different writing papers by means of artificial aging (100 °C, 3 days), while a part of the original material was stored in a box for future research. From the results of later studies it was concluded that only a qualitative relation between the effects of artificial aging and the natural aging of the original paper that had taken place in the meantime could be demonstrated (Wilson 1955).

In a more recent study Wilson and Parks (1980) compared the changes in properties after 36 years of natural aging with the results of artificial aging (100 °C, 3 days) of the original material in 1937. With some types of paper, changes in folding endurance, tear resistance and several chemical characteristics that had occurred in natural aging appeared to correspond reasonably well with those obtained by means of artificial aging. Other types of paper showed more deviations.

An elegant approach of the comparison between natural and artificial aging can be found in the current research of Erhardt and other co-workers from the Smithsonian Center for Materials Research and Education (SCMRE) in Suitland, USA (Erhardt 1987, 1988, 1993, 1995). The starting-point in their studies is that the results of artificial aging can only lead to reliable predictions with regard to natural aging if the artificial aging method speeds up the rate of deterioration of paper without fundamentally changing the nature of the process. This means that every individual reaction involved in the decay ought to be accelerated by the same factor, keeping the ratio between the reaction velocities constant. Extended comparison of the effects of different artificial aging methods, monitoring the various degradation reactions separately by means of sensitive measuring equipment, led to the interesting conclusion that the nature of the paper deterioration process is a function of relative humidity (RH) rather than temperature. By changing the temperature at a constant RH value, the rate of the deterioration process is altered without fundamental changes in the process itself, so that the same level of aging can be obtained at different temperatures, simply by adjusting the duration of the treatment. However, a change in RH, leaving the temperature constant, results in a different proportion between the rates of the individual reactions and consequent changes in the distribution of reaction products, which makes it impossible to reach the same level of aging at different RHs. If one extends this conclusion, drawn from investigations on different artificial aging methods, to the simulation of natural aging, it would seem advisable to apply the artificial aging at the same relative humidity as at the storage conditions under which the natural aging takes place.

Comparison of identical copies of books

Another interesting line of research in this context is the comparison of identical copies of books which, as part of separate library collections, have been stored under different conditions and as a consequence show different stages of deterioration. Although this kind of research does not result directly into recommendations for artificial aging, as it actually concerns a compa-

ri-son of two different ways of natural aging, relevant information can still be obtained. Besides offering more insight into environmental effects on the rate of natural aging of paper, these studies results also indicate which environmental factors are responsible for the difference in aging condition and thus in rate of decay.

In this way, comparative investigations of this kind can indirectly be of importance for the development of reliable artificial aging methods. The study on pairs of books from the New York Library (NYPL) and the Koninklijke Bibliotheek (KB), performed by the KB in collaboration with TNO Paper & Board Research (Delft), showed that the paper in the NYPL copies deteriorated faster due to a higher concentration of the air pollutant sulfur dioxide, in combination with low and/or fluctuating relative humidities in the NYPL storage rooms (Pauk 1996b; Havermans 1997a). Indications for a role of air pollution in the development of differences in book pairs have also been found in previous comparative studies (Hudson 1967; Smith 1972; Baer 1986).

Long-term storage projects

Useful information on the rate of paper deterioration and on the storage conditions which play an important role in this respect, can also be expected from a current research project of the General State Archives in The Hague (Feber 1998). In this study, which the Koninklijke Bibliotheek has joined through the SALTO-project ('studie *aangaande lange termijn opslag*', study concerning long-term storage), identical archive and library materials and other test papers are stored at two locations, one of which is provided with an installation to filter air pollutants. By means of continuous registration of environmental conditions like temperature, humidity and concentrations of air pollutants, as well as frequent analysis of the quality of the stored material in both storage rooms, interesting data will become available in the course of time. These data will offer more insight into the long-term effects of air filtering, and they will also give a realistic indication of the rate at which the various types of paper deteriorate under different degrees of air pollution.

Damage surveys

The analysis of the data resulting from damage surveys has resulted in other comparative studies. In the last decades these surveys have been performed worldwide in many archives and libraries, primarily in order to gain a better understanding of the nature and extent of paper degradation. By repeating such surveys after a certain time interval, re-examining the same test materials, and by comparison of the results with the findings of the earlier tests, an indication can be obtained of the rate with which certain paper properties have changed in the meantime. For example, a damage survey from 1990 at the Koninklijke Bibliotheek was repeated on a limited scale in 1996, clearly showing that a measurable decrease in folding endurance had occurred already in the course of six years. However, due to the limitations of this investigation, definite statements about the rate of paper decay could not be made (Hol 1990; Pauk 1997).

Historical approach

Finally it is worth mentioning that an historical approach also appears to create possibilities for acquiring insight into the natural aging rate of paper. In recent studies into historical sources on the inferior quality of nineteenth-century Dutch paper, this approach has been elaborated. It is argued that the results of contemporary mid-nineteenth century scientific investigations into paper quality and comparison of these data with the findings of present-day examination of the same material, traced in archival collections, in principle produce useful indications of the rate of paper decay (Grijn 1996, 1998; Porck 1996).

Discussion

Evaluation

'Artificial aging' is a test in general use and the term a common one in conservation research. This seems to suggest (i) that there exists a normal, natural aging process, (ii) that this process can be artificially accelerated without changing in its nature, and (iii) that by using artificial aging tests meaningful information on this natural aging process can be obtained. The present study shows that all of these suggestions can be seriously questioned.

Insufficient knowledge on natural aging

In the first place there is no generally valid description of the normal, natural aging process of paper. There are so many paper-dependent internal factors, partly as yet unknown, as well as external factors varying with time and place that influence the stability of paper that it seems impossible to predict unambiguously the natural aging of a particular sheet of paper (Roberson 1981; Wilson 1983; Fellers 1989; Feller 1994a,b; Gurnagul 1994; Norris 1994). Still more complex is the situation in a stack of paper, like a book or a file, let alone a complete library or archive collection. A reliable judgement on the nature and rate of natural aging can actually be made only afterwards, i.e. deduced in retrospect. Moreover this is only possible if detailed information is available on the original material condition of the object and on the storage conditions to which the object has been exposed in the course of time. The examples of comparative studies on identical copies of books stored under different conditions, mentioned in the preceding section, show that such a reconstruction of the storage history of collections is no sinecure.

Simulation by stimulation?

In the second place it is probably only wishful thinking that natural aging of paper can be simply accelerated by exposure to artificial, laboratory conditions, and that in this way certain forms of damage, familiar from the conservation practice, can be reliably simulated. The complex character of the natural aging process, which is partly still obscure, can never be completely achieved experimentally. Even if natural aging could be simplified to the effects of the paper degradation reactions as known today, it is highly doubtful that artificial stimulation of these reactions, by means of certain adjustments of environmental parameters in a climate-chamber, will result in an identical condition of the paper in the short term as would result from the natural aging process in the long term. Such an assumption is as yet insufficiently verified by scientific research. The current uncertainty in this regard is clearly illustrated by the multitude of standard and 'home' methods for artificial aging mentioned above. Artificial aging is performed at different temperatures, different humidities, sometimes in the presence of air pollutants or other 'stimuli' and sometimes not, and for different periods of time. Even the standard methods for artificial aging, developed in order to counteract this large variation, do not resolve this: the international ISO-standards, for example, developed in the eighties, leave the possibility open to age artificially at different temperatures and relative humidities.

Relevance of artificial aging

All this implies that quite a few objections can be put forward against the idea that artificial aging presents relevant data for the determination of the nature and rate of the natural aging of paper. The studies into the reliability, i.e. predictive value of artificial aging, as described above, have not yet resulted in a conclusion that is generally endorsed, nor into the use of a generally accepted method. The findings of the few investigations performed in this respect have not yet sufficiently proven in practice that the theoretical basis for the application of artificial aging is indeed valid. Nor have these studies resulted in adjustments of current methods. The limited scale of the research into the comparison of artificial and natural paper aging is remarkable. However complex this kind of investigation may be, it is one of the few possibilities to attune the procedure of artificial aging to the natural aging process. In the field of leather conservation, for example, this approach appears to have been rather successful (Larsen 1994).

Problem of reliability

The small number of research projects that have tried to verify the predictive value of artificial aging analysis strongly contrasts with the widespread use of this analysis in practice. Even so, this does not mean there is no concern about the issue. The problem of the reliability of artificial aging has been raised frequently in the specialist literature (Arney 1980; Bansa 1984, 1992, 1998a; Mokken 1987; Erhardt 1988; Ströfer-Hua 1990; Wypych 1990; Brown 1991; Feller 1994a; Shahani 1994; Havermans 1997b). The present insecurity about the value of artificial aging can for instance be illustrated from the fact that the international standard ISO-9706 for permanent paper, in which a prediction of the durability and permanence would be extremely desirable, does not include an artificial aging test (Berkhout 1994).

In view of the different objectives with which artificial aging is applied, the Arrhenius-test, aimed at a quantitative statement on permanence, i.e. rate of paper decay, will probably be the most debatable. In the case of other applications, like the determination of the qualitative effect of a conservation treatment, the investigation of a certain degradation reaction or the simulation of specific kinds of damage, the strict prerequisite for the Arrhenius-test, namely that all natural deterioration reactions must be accelerated by one and the same factor, does not need to be fulfilled. In these cases it will be more likely that artificial aging may produce trustworthy indications. Still, here too reservations should be made because on the basis of the present state of knowledge, it cannot be excluded that unrealistic effects will occur as a consequence of undesirable reactions, i.e. reactions absent in the natural aging process.

Deadlock

With regard to artificial aging there seems to have developed a kind of deadlock in the conservation science community, and sometimes even an obvious reluctance to exchange experience and to strive for a joint approach to tackle the problem. This reluctance, which perhaps also caused the limited response to the discussion planned for the present study, can be explained to some extent. A critical discussion of such crucial and historically deeply rooted issues may lead to changes in opinions that can have far-reaching consequen-

ces. It is possible that decisions taken in the past, either in conservation policy or conservation practice, based on the results of artificial aging tests, are undermined in such a discussion. On the other hand the current deadlock is a cause for serious regret, as it obstructs a solution of the many questions on artificial aging which are still left unanswered. In the meantime the natural aging of paper proceeds without mercy.

Conclusions

In summary, four conclusions can be drawn on the basis of this evaluation of the current state of affairs with respect to the theory and practice of artificial aging of paper:

The rate of paper deterioration and other quantitative aspects of the natural aging of paper, such as durability and permanence, cannot be reliably predicted by means of the present artificial aging tests.

The application of artificial aging can be relevant and meaningful with respect to:

- a. the determination of the qualitative effect of a certain paper conservation treatment;
- b. fundamental research into paper degradation reactions;
- c. the simulation of specific types of paper damage.

The amount of research into the predictive value of artificial aging of paper is not sufficient and the results are not adequately used for the improvement of artificial aging methods.

Reluctance in discussion and maintenance of a *status quo* characterize the conservation science community with regard to the problem of artificial aging. As a consequence the solution of this problem is seriously hindered.

Recommendations

The present study is intended as an overview and evaluation of the current state-of-the-art rather than an elaboration of solutions. However, several recommendations can be made which may contribute to the improvement of the current situation of uncertainty and doubt.

The exchange of knowledge and experience in the field of artificial aging analysis of paper among conservation scientists and policy makers needs to be improved. A special workshop on this subject, under the auspices of the European Commission on Preservation and Access, the Koninklijke Bibliotheek in cooperation with the Netherlands Institute for Cultural Heritage, or the Council on Library and Information Resources may offer a suitable framework for such a discussion.

Research to verify the hypothesis that artificial aging produces meaningful data to predict the effects of natural aging of paper should be continued and subsequently be 'translated' in improved, i.e. more reliable artificial aging tests.

Comparative investigation of natural and artificial aging of paper can be performed in parallel with long-term studies into natural paper deterioration, by means of artificial aging treatments and subsequent analysis of part of the initial test material. The findings can be compared in a later stage, by a next generation of conservation scientists, with those of the naturally aged material.

It is recommended that statements on the rate of the natural aging of a certain kind of paper are not only limited to predictions for the future by means of artificial aging. In some cases, a retrospective approach is possible, using historical sources that present detailed information on the quality of a specific type of paper in the past.

In the application of the current artificial aging tests for the determination of the relative effects of a certain paper conservation treatment, for the investigation of a specific degradation mechanism, or for the simulation of a certain form of paper decay, a 'mild' artificial aging method is to be preferred because of the inevitable risk of undesirable degradation reactions, that is to say reactions that do not occur under natural conditions. Artificial aging conditions should therefore in principle be kept as closely as possible to normal, natural conditions.

As false expectations may be evoked by the term 'artificial aging' it should be considered:

- a. to limit the use of the term 'aging' to the genuine process of natural aging;
- b. to use another term for the so-called artificial aging test, like 'artificially induced degradation (AID-) test', which reflects the way in which these tests are commonly used in practice: choosing and adjusting the environmental conditions in such a way that a measurable deterioration of the material takes place in a relatively short time.

References

- Arney, J.S., Jacobs, A.J. (1979). Accelerated Aging of Paper. The Relative Importance of Atmospheric Oxidation. *Tappi* 62(7), p. 89-91.
- Arney, J.S., Jacobs, A.J. (1980). Newsprint Deterioration. The Influence of Temperature on the Relative Contribution of Oxygen-independent and Oxygen-dependent Processes in the Total Rate. *Tappi* 63(1), p. 75-77.
- Arney, J.S., Chapdelaine, A.H. (1981). A Kinetic Study of the Influence of Acidity on the Accelerated Aging of Paper. In (Williams, J.C., eds.): *Preservation of Paper and Textiles of Historic and Artistic Interest. II*. American Chemical Society (Advances in Chemistry Series 193), Washington DC, p. 189-204.
- Arnold, R.B. (1996). Update: ASTM/ISR Paper Aging Research Program. *The Abbey Newsletter* 20(3), p. 29-30.
- ASTM (1971). *Standard Test for Relative Stability of Paper (Effect of Heat on Folding Endurance)*. American Society for Testing and Materials (ASTM-D776-65, revised 1971; 72 hours at 105±2 °C).
- ASTM (1987). *Standard Test Method for Determination of Effect of Dry Heat on Properties of Paper and Board*. American Society for Testing and Materials (ASTM-D776-87; 72 hours at 105±2 °C).
- Back, E.L., Klinga, L.O. (1963). Reactions in Dimensional Stabilization of Paper and Fibre Building Board by Heat Treatment. *Svensk Papperstidning* 66(19), p. 745-753.
- Back, E.L. (1967a). Thermal Auto-crosslinking in Cellulose Material. *Pulp and Paper Magazine of Canada* 68(4), p. T165-T171.
- Back, E.L., Thong Htun, M., Jackson, M., Johanson, F. (1967b). Ultrasonic Measurements of the Thermal Softening of Paper Products and the Influence of Thermal Auto-crosslinking Reactions. *Tappi* 50(11), p. 542-547.
- Baer, N.S., Indictor, N. (1974). An Examination of Test Methods for the Evaluation of Papers and Paper Conservation Materials. *Archief- en Bibliotheekwezen in België* 12 (extra issue: Studies over restauratie van archief, boeken en handschriften), p. 17-30.
- Baer, N.S., Indictor, N. (1977). Use of the Arrhenius Equation in Multicomponent Systems. In (Williams, J.C., eds.): *Preservation of Paper and Textiles of Historic and Artistic Value*. American Chemical Society (Advances in Chemistry Series 164), Washington DC, p. 336-351.
- Baer, N.S., Berman, S.M. (1986). An Evaluation of the Statistical Significance of Hudson's Acidity Data for 17th & 18th Century Books in Two Libraries. *Restaurator* 7, p. 119-124.
- Baker, C.A. (1991). Methylcellulose and Sodiummethylcellulose: an Evaluation for Use in Paper Conservation through Accelerated Aging. In (Brommelle, N.S., Pye, E.M., Smith, P., Thomson, G., eds.): *Adhesives and Consolidants. Preprints of the Contributions to the Paris Congress, 2-8 September 1984*. International Institute for Conservation of Historic and Artistic Works (IIC), London, p. 55-59.
- Banik, G. (1982). Naturwissenschaftliche Untersuchungen zur Aufklärung des Kupferfrasses in graphischen Kunstwerken. *Das Papier* 36(9), p. 438-448.

- Banik, G., Sobotka, W.K., Vendl, A., Norzsicska, S. (1993). Effects of Atmospheric Pollutants on Deacidified Modern Papers. In (Bridgland, J., ed.): *Preprints. 10th Triennial Meeting, Washington DC, USA, 22-27 August 1993*. ICOM Committee for Conservation, Paris, p. 435-441.
- Bansa, H., Hofer, H.H. (1984). Die Aussagekraft einer künstlichen Alterung von Papier für Prognosen über seine zukünftige Benutzbarkeit. *Restaurator* 6, p. 21-60.
- Bansa, H. (1992). Accelerated Aging Tests in Conservation Research: Some Ideas for a Future Method. *Restaurator* 13, p. 114-137.
- Bansa, H., Ishii, R. (1997). The Effect of Different Strengthening Methods on Different Kinds of Paper. *Restaurator* 18, p. 51-72.
- Bansa, H. (1998a). Aqueous Deacidification – with Calcium or with Magnesium? *Restaurator* 19, p. 1-40.
- Bansa, H. [Bayerische Staatsbibliothek, München] (1998b): personal communication.
- Barrett, T.D. (1989). *Early European Papers/Contemporary Conservation Papers. A Report on Research Undertaken from Fall 1984 through Fall 1987*. The Paper Conservator 13, p. 57-65.
- Barrett, T. (1992). Evaluating the Effect of Gelatin Sizing with Regard to the Permanence of Paper. In (Fairbrass, S., ed.): *Conference Papers, Manchester, 1992*. Institute of Paper Conservation, Leigh, p. 228-233.
- Barrow, W.J. (1963). *Permanence/Durability of the Book. A Two-year Research Program*. W.J. Barrow Research Laboratories, Richmond.
- Barrow, W.J. (1964). *Permanence/Durability of the Book. II. Test Data of Naturally Aged Papers*. W.J. Barrow Research Laboratories, Richmond.
- Berkhout, S.A. (1994). *Beoordeling en vergelijking van drie duurzaamheidsnormen voor papier*. TNO (TNO-report PK 94.7009), Delft.
- Brandis, L., Lyall, J. (1997). Properties of Paper in Naturally Aged Books. *Restaurator* 18, p. 115-130.
- Brown, R.P. (1991). Survey of Status of Test Methods for Accelerated Durability Testing. *Polymer Testing* 10, p. 3-30.
- Browning, B.L., Wink, W.A. (1968). Studies on the Permanence and Durability of Paper: the Prediction of Paper Permanence. *Tappi* 51, p. 156-163.
- Browning, B.L. (1969). *Analysis of Paper*. Marcel Dekker, New York, p.314-317.
- Daniel, F., Flieder, F., Leclerc, F. (1992). The Behaviour of Papers Deacidified under Pressure by Ethylmagnesium Carbonate as Regards two Kinds of Accelerated Aging: Wet Heat and Simulated Pollution. In (Kastaly, B., ed.): *Papers of the Conference on Book and Paper Conservation, Held in Budapest, 4-7 September 1990*. TAPPI, National Széchényi Library, Budapest, p. 471-482.
- Daniels, V.D., Shashoua, Y.R. (1993). The Effect of Gum Arabic Solubility on the Washing of Watercolours. In (Bridgland, J., ed.): *Preprints. 10th Triennial Meeting, Washington DC, USA, 22-27 August 1993*. ICOM Committee for Conservation, Paris, p. 442-446.
- Down, J. [Canadian Conservation Institute (CCI), Ottawa] (1998): personal communication about the discussions in the CCI on the subject of artificial aging.

- Erhardt, D., Endt, D.v., Hopwood, W. (1987). The Comparison of Accelerated Aging Conditions through the Analysis of Artificially Aged Paper. In: *Preprints of Papers Presented at the Fifteenth Annual Meeting, Vancouver, British Columbia, Canada, May 20-24, 1987*. American Institute for Conservation, Washington DC, p. 43-55.
- Erhardt, D. (1988). Paper Degradation: a Comparison of Industrial and Archival Concerns. In: *1988 Paper Preservation Symposium*. TAPPI Press, Atlanta, p. 83-90.
- Erhardt, D. (1989). Relationship of Reaction Rates to Temperature. *The Abbey Newsletter* 13(3), p. 38-39.
- Erhardt, D. (1993). Temperature and Relative Humidity Effects on the Aging of Cellulose. In (Beyer, C., ed.): *Preservation Research and Development. Round Table Proceedings, September 29-29, 1992*. Library of Congress Preservation Directorate, Washington DC, p. 31-34.
- Erhardt, D., Mecklenburg, M.F. (1995). Accelerated vs Natural Aging: Effect of Aging Conditions on the Aging Process of Cellulose. In (Vandiver, P.B., Druzik, J.R., Madrid, J.L.G., Freestone, I.C., Wheeler G.S., eds.): *Materials Issues in Art and Archeology. IV. Symposium Held May 16-21, 1994, Cancun*. Materials Research Society (Materials Research Society Symposium Proceedings 352), Pittsburgh, p. 247-270.
- Erhardt, D. [Smithsonian Center for Materials Research and Education, Suitland, MD] (1998): personal communication.
- Ernst, U. (1989). Alterungsverhalten von Schreib-, Druck- und Kopierpapieren. *ARBIDO-R4* 4, p. 99-105.
- Feber, M.d., Havermans, J., Cornelissen, E. (1998). The Positive Effects of Air Purification in the Dutch State Archives. Part I: Experimental Set Up and Air Quality. *Restaurator* 19, p. 212-223.
- Feller, R.L., Wilt, M. (1990). *Evaluation of Cellulose Ethers for Conservation*. The Getty Conservation Institute (Research in Conservation 3), Marina del Rey.
- Feller, R.L. (1994a). *Accelerated Aging. Photochemical and Thermal Aspects*. The Getty Conservation Institute (Research in Conservation 4), Marina del Rey.
- Feller, R.L. (1994b). Aspects of Chemical Research in Conservation: the Deterioration Process. *Journal of the American Institute for Conservation* 33, p. 91-99.
- Fellers, C., Iversen, T., Lindström, T., Nilsson, T., Rigdahl, M. (1989). *Aging/Degradation of Paper. A Literature Survey*. FoU-projektet för papperskonservering (Report 1E), Stockholm.
- Fink, P., Zwicky, K. (1965). Untersuchungen über die Lagerbeständigkeit von Druckpapieren. *Textil-Rundschau* 20(10), p. 289-305.
- Flieder, F., Leclerc, F. (1992). Influence of Optical Brighteners on Paper Permanence. In (Fairbrass, S., ed.): *Conference Papers Manchester 1992*. Institute of Paper Conservation, Leigh, p. 257-263.
- Fung, D.P.C. (1969). Kinetics and Mechanism of the Thermal Degradation of Cellulose. *Tappi* 52(2), p. 319-321.
- Graminski, E.L. (1970). The Stress-strain Behavior of Accelerated and Naturally Aged Papers. *Tappi* 53(3), p. 406-410.
- Graminski, E.L., Parks, E.J., Toth, E.E. (1979). The Effects of Temperature and Moisture on the Accelerated Aging of Paper. In (Eby, R.K., ed.):

- Durability of Macromolecular Materials*. American Chemical Society (ACS Symposium Series 95), Washington DC, p. 341-355.
- Gray, G.G. (1969). An Accelerated-aging Study Comparing Kinetic Rates vs. TAPPI Standard 453. *Tappi* 52(2), p. 325-334.
- Gray, G.G. (1977). Determination and Significance of Activation Energy in Permanence Tests. In (Williams, J.C., ed.): *Preservation of Paper and Textiles of Historic and Artistic Value*. American Chemical Society (Advances in Chemistry Series 164), Washington DC, p. 286-313.
- Grijn, E.v.d., Kardinaal, A., Porck, H. (1996). *The 1845 Paper Crisis in the Netherlands. An Historical-technical Study into the Dutch Paper Market and into the Nature and Extent of the Inferior Quality of Mid-19th Century Paper*. Paper presented at Congress 23 of the IPH (International Association of Paper Historians), Leipzig. IPH-Yearbook 1996, p. 153-163.
- Grijn, E.v.d., Kardinaal, A., Porck, H. (1998). *The Evaluation of Paperdegradation: the Historical and the Scientific Approach*. Paper presented at Congress 24 of the IPH (International Association of Paper Historians), Porto. IPH-Yearbook 1998, in press.
- Gurnagul, N., Howard, R.C., Zou, X., Uesaka, T., Page, D.H. (1994). The Mechanical Permanence of Paper: a Literature Review. In: *Proceedings of the Workshop on the Effects of Aging on Printing and Writing Papers*. ASTM Institute for Standards Research, Philadelphia, p. 235-257.
- Hall, G. (1926). *Permanence of Paper*. Technical Assoc. Papers, Series IX, p.92
- Hanus, J., Komornikova, M. (1987). The Application of Statistical Analysis in Evaluation of Changes in Some Properties of Aged Papers. *Archief en Bibliotheekwezen in België* 58(1-2), p.161-182.
- Hanus, J., Komornikova, M., Minarikova, J. (1995). Influence of Boxing Materials on the Properties of Different Paper Items Stored Inside. *Restaurator* 16, p. 194-208.
- Hanus, J., Komornikova, M., Minarikova, J. (1996). Changes in Some Mechanical Properties of Paper During Aging in an Archival Box. In (Bridgland, J., ed.): *11th Triennial Meeting Edinburgh, Scotland 1-6 September 1996. Preprints Volume II*. ICOM Committee for Conservation, Paris, p. 510-516.
- Havermans, J.B.G.A. (1992). *Vergelijkend onderzoek naar de houdbaarheid van papier onder gangbare klimatologische omstandigheden en papier bewaard in een inert gas*. TNO (TNO-report PK 92.1047), Delft.
- Havermans, J.B.G.A. (1994). STEP CT90-0100. The Effects of Air Pollutants on Accelerated Aging of Cellulose Containing Materials: Paper. Preliminary Results. / Main Conclusions of the STEP CT 90-0100 Project. Influences of Air Pollutants on the Accelerated Aging of Cellulose Based Materials 'Paper'. In: *Proceedings of the Workshop on the Effects of Aging on Printing and Writing Papers*. ASTM Institute for Standards Research, Philadelphia, p. 159-195.
- Havermans, J. (1995). Effects of Air Pollutants on the Accelerated Aging of Cellulose-based Materials. *Restaurator* 16, p. 209-233.
- Havermans, J.B.G.A. (1997a). *A Study of the Cause of Damage on Pairs of Books*. TNO (TNO-report BU2.97/009063-1/JH), Delft.
- Havermans, J. (1997b). Durability of Information – From Stone to Polymer. In (Fellows-Jensen, G., Springborg, P., eds.): *Care and Conservation of Manuscripts 3. Proceedings of the Third International Seminar on the Care and*

- Conservation of Manuscripts Held at the University of Copenhagen 14th-15th October 1996*. The Royal Library, Copenhagen, p. 99-106.
- Herzberg, W. (1899). Einfluss höherer Wärmegrade auf die Festigkeitseigenschaften von Papier. *Papier-Zeitung* 24(61), p. 2343.
- Hofenk de Graaff, J.H., Roelofs, W.G.Th. (1994). Investigation of the Long-term effects of Ethylene Oxide and Gamma Rays on the Aging of Paper. In (Verschoor, H., Mosk, J., eds.): *Contributions of the Central Research Laboratory to the Field of Conservation and Restoration*. Central Research Laboratory for Objects of Art and Science, Amsterdam, p. 53-64.
- Hofmann, C., Reyden, D.v.d., Baker, M. (1992). The Effect of Three Humidification, Flattening and Drying Techniques on the Optical and Mechanical Properties of New and Aged Modern Transparent Papers. In (Fairbrass, S., ed.): *Conference Papers Manchester 1992*. Institute of Paper Conservation, Leigh, p. 247-256.
- Hol, R.C., Voogt, L. (eds.) (1991). *Bedreigd papierbezit in beeld. Schade-inventariserend onderzoek van archief- en bibliotheekmateriaal van na 1800 bij het Algemeen Rijksarchief en de Koninklijke Bibliotheek / Endangered Books and Documents. A Damage Survey of Post-1800 Archive and Library Material Held by the General Archives of the Netherlands and the Koninklijke Bibliotheek (National Library of the Netherlands)*. Coördinatiepunt Nationaal Conserveringsbeleid (CNC-Publikaties, 2), Den Haag.
- Hudson, F.L. (1967). Acidity of 17th & 18th Century Books in Two Libraries. *Paper Technology* 8, p. 189-190.
- Inaba, M., Sugisita, R. (1992). *The Deterioration of Japanese Paper by Accelerated Aging Treatment*. Third International Institute of Paper Conservation Conference, University of Manchester Institute of Science and Technology, 1-4 april.
- ISO (1982). *Paper and Board. Accelerated Aging, Part 1: Dry Heat Treatment*. International Standards Organization (ISO-5630/1; 72 hours at 105±2 °C).
- ISO (1985). *Paper and Board. Accelerated Aging, Part 2: Moist Heat Treatment at 90 °C and 25% Relative Humidity*. International Standards Organization (ISO-5630/2; 24, 48, 72 en 144 hours at 90±0.2 °C en 25±0.5% RH).
- ISO (1986a). *Paper and Board. Accelerated Aging, Part 3: Moist Heat Treatment at 80 °C and 65% Relative Humidity*. International Standards Organization (ISO-5630/3; 24, 48, 72 en 144 hours at 80±0.5 °C and 65±1% RH).
- ISO (1986b). *Paper and Board. Accelerated Aging, Part 4: Dry Heat Treatment at 120 °C or 150 °C*. International Standards Organization (ISO-5630/4; method A: 168 hours at 120±2 °C, method B: 24 hours at 150±2 °C).
- Kaminska, E.M., Burgess, H.D. (1994). *Evaluation of Commercial Mass Deacidification Processes: AKZO-DEZ, Wei T'O and FMC-MG3. Phase II. New and Artificially Aged Modern Papers*. Canadian Conservation Institute, Ottawa.
- Kantrowitz, M.S., Spencer, E.W., Simmons, R.H. (1940). *Permanence and Durability of Paper, an Annotated Bibliography of the Technical Literature 1855 AD to 1939 AD*. US Government Printing Office Division of Tests and Technical Control (Technical Bulletin 22), Washington DC.

- Langwell, W.H. (1955). The Permanence of Paper in Temperate Climates. *Tappi* 38(9), p. 190A-192A.
- Larsen, R. (ed.) (1994). *STEP Leather Project. Evaluation of the Correlation between Natural and Artificial Aging of Vegetable Tanned Leather and Determination of Parameters for Standardization of an Artificial Aging Method.* (EC-DG XII, STEP Project CT 90-0105). Bjarnholt Repro, Copenhagen.
- Launer, H.F., Wilson, W.K. (1943). Photochemical Stability of Papers. *Journal of Research of the National Bureau of Standards* 30, p. 55-74.
- Leclerc, F., Flieder, F. (1993a). Influence des azurants optiques sur la permanence des papiers. In: *Les documents graphiques et photographiques. Analyse et conservation. Travaux du Center de Recherche sur la Conservation des Documents Graphiques 1991-1993.* Archives Nationales, Paris, p. 207-222.
- Leclerc, F., Duhamel, M., Valette, N. (1993b). Etude sur la stabilité des photocopies. In: *Les documents graphiques et photographiques. Analyse et conservation. Travaux du Center de Recherche sur la Conservation des Documents Graphiques 1991-1993.* Archives Nationales, Paris, p. 223-246.
- Letnar, M.C., Vodopivec, J. (1997). Influence of Paper Raw Materials and Technological Conditions of Paper Manufacture on Paper Aging. *Restaurator* 18, p. 73-91.
- Lindström, T. (1989). Comparison between Natural and Accelerated Aging of Paper. In: Fellers, C., Iversen, T., Lindström, T., Nilsson, T., Rigdahl, M. *Aging/Degradation of Paper. A Literature Review.* FoU-projektet för Papperskonservering (Report 1E), Stockholm, p. 123-131.
- Luner, P. (1969). Paper Permanence. *Tappi* 52(5), p. 796.
- Maraval, M., Flieder, F. (1993). La stabilité des encres d'imprimerie. In: *Les documents graphiques et photographiques. Analyse et conservation. Travaux du Center de Recherche sur la Conservation des Documents Graphiques 1991-1993.* Archives Nationales, Paris, p. 163-205.
- Medved, Z.N., Kozlov, N.A., Tarakanov, O.G. (1973). Changes of Certain Properties of Cellulose During Aging. *Zhurnal Prikladnoi Khimii* 46(5), p. 1103-1107. (Translation: Consultants Bureau, Plenum Publishing Corporation, New York, 1973).
- Mendenhall, G.D., Kelly, G.B., Williams, J.C. (1981). The Application of Several Empirical Equations to Describe the Change of Properties of Paper on Accelerated Aging. In (Williams, J.C., ed.): *Preservation of Paper and Textiles of Historic and Artistic Interest. II.* American Chemical Society (Advances in Chemistry Series 193), Washington DC, p. 177-188.
- Mokken, M., Steemers, T., Lingbeek, N. (1987). *Versnelde papierveroudering.* Een literatuurstudie in het kader van de HBO-opleiding Papier- en Boekrestauratie, Amsterdam; Vakbibliotheek Conservering (L 689), Koninklijke Bibliotheek, Den Haag.
- Neevel, J.G., Reissland, B. (1997). The Ink Corrosion Project at the Netherlands Institute for Cultural Heritage – a Review. In (Windt, H.v.d., ed.): *Iron-gall Ink Corrosion. Proceedings European Workshop on Iron-gall Ink Corrosion.* Museum Boijmans van Beuningen, Rotterdam, Netherlands Institute for Cultural Heritage, Amsterdam, p. 37-45.

- Neimo, L. (1964). Accelerated Heat Aging of Cellulose. *Paperi Ja Puu-Papper och Tra* 46, p. 7-9, 11-14 (Translation: Institute of Paper Chemistry, Appleton, 1964).
- NEN (1983). *Paper en karton. Bepaling van de verandering in eigenschappen met behulp van versnelde veroudering door droge verhitting*. Nederlands Normalisatie-instituut (Norm NEN-1855; 1-3 days at 105±2 °C).
- Norris, T.O. (1994). Overview of Paper Deterioration. In: *Proceedings of the Workshop on the Effects of Aging on Printing and Writing Papers*. ASTM Institute for Standards Research, Philadelphia, p. 14-21.
- Parks, E.J., Hebert, R.L. (1971a). *Accelerated Aging of Laboratory Handsheets: Retention of Folding Endurance, Internal Tear, Bursting Strength, and Tensile Strength*. National Bureau of Standards (NBS Report 10-628), Washington DC.
- Parks, E.J., Hebert, R.L. (1971b). *Accelerated Aging of Laboratory Handsheets: Changes in Acidity, Fiber Strength, and Wet Strength*. National Bureau of Standards (NBS Report 10-627), Washington DC.
- Parks, E.J., Hebert, R.L. (1972). *Accelerated Aging of Laboratory Handsheets: Reflectance, Moisture Regain, Sonic Modulus, and Differential Thermal Analysis*. National Bureau of Standards (NBS Report 10-687), Washington DC.
- Pauk, S., Porck, H. (1993). *Een oriënterend onderzoek naar de invloed van insealen op papier bij kunstmatige veroudering*. Koninklijke Bibliotheek (KB Extra 7), Den Haag / De invloed van verschillende folies en verschillende manieren van insealen op papier bij kunstmatige veroudering. *De Restaurator* 23, p. 56-57.
- Pauk, S., Porck, H. (1994). *Oriënterend onderzoek naar de effecten van de Battelle en diethylzink massaontzuringmethoden / Pilot Research into the Effects of the Battelle and Diethylzinc Massdeacidification Methods*. Coördinatiepunt Nationaal Conserveringsbeleid (CNC-Publikaties,8), Den Haag.
- Pauk, S. (1996a). *De Bookkeeper massaontzuring. Enkele effecten op 20^e-eeuws bibliotheekmateriaal / The Bookkeeper Mass Deacidification. Some Effects on 20th Century Library Materials*. Koninklijke Bibliotheek, Den Haag.
- Pauk, S., Porck, H. (1996b). *Land om land. Verslag van de bestudering van identieke boekenparen, die onder verschillende omstandigheden zijn bewaard*. Koninklijke Bibliotheek, Den Haag.
- Pauk, S. (1997). *Bedreigd papierbezit nogmaals in beeld. Beperkte herhaling van het schade-inventariserend onderzoek uit 1990*. Koninklijke Bibliotheek, Den Haag.
- Pearlstein, E.J., Cabelli, D., King, A., Indictor, N. (1982). Effects of Eraser Treatment on Paper. *Journal of the American Institute for Conservation* 22, p. 1-12.
- Porck, H.J., Smit, W.J.Th. (1990). Schade-inventarisatie bij krantenmateriaal. *Open* 22, p. 160-162.
- Porck, H., Grijn, E.v.d., Kardinaal, A. (1996). *Analysis of Paper Destabilizing Factors in Mid-19th Century Paper Production. A Contribution to the Development of a Conservation Policy*. Paper presented at Congress 23 of the IPH (International Association of Paper Historians), Leipzig. IPH-Yearbook 1996, p. 164-167.

- Porck, H.J. (1999). *Snelheid van papierverval. De betrouwbaarheid van prognoses op basis van kunstmatige-verouderingstests*. Koninklijke Bibliotheek (Metamorfoze-report), Den Haag.
- Pravilova, T.A. (1964). Aging of Paper. In (Solechnik, N.Y., ed.): *New Methods for the Restoration and Preservation of Documents and Books*. (USSR Academy of Sciences). Translation: Israel Program for Scientific Translations Ltd. (IPST Catalogus 1024), Jerusalem. Oldbourne Press, London, p. 69-78.
- Priest, D.J., Sule, A. (1992). Measuring the Physical Properties of Paper within Books. In (Fairbrass, S., ed.): *Conference Papers Manchester 1992*. Institute of Paper Conservation, Leigh, p. 146-152.
- Rahn, K.D. (1974). Zur Beurteilung der Alterungsbeständigkeit von Papier aus der Sicht des Papierherstellers. *Archief- en Bibliotheekwezen in België* 12 (extra issue: Studies over restauratie van archief, boeken en handschriften), p. 119-130.
- Rasch, R.H. (1929). Quality of Purified Wood Fibers. *Paper Trade Journal* 88 (21 febr.), p. 233-268 (TAPPI Section p. 125-145).
- Reyden, D.v.d., Hofmann, C., Baker, M. (1992). Some Effects of Solvents on Transparent Papers. In (Fairbrass, S., ed.): *Conference Papers Manchester 1992*. Institute of Paper Conservation, Leigh, p. 234-246.
- Richter, G.A., Wells, F.L. (1956). Influence of Moisture in Accelerated Aging of Cellulose. *Tappi* 39(8), p. 603-608.
- Roberson, D.D. (1981). Permanence/Durability and Preservation at the Barrow Laboratory. In (Williams, J.C. ed.): *Preservation of Paper and Textiles of Historic and Artistic Interest. II*. American Chemical Society, Washington DC, p. 45-55.
- Roelofs, W.G.Th., Hofenk de Graaff, J.H., Knoppe, M. (1994). *Onderzoek naar de mogelijkheid archiefmateriaal, boeken en andere voorwerpen van culturele waarde te beschermen tegen luchtverontreiniging door het gebruik van gebufferde dozen en omslagen. Deel I. Onderzoek naar de veroudering van papier in stapels*. Centraal Laboratorium voor Onderzoek van Voorwerpen van Kunst en Wetenschap (Project 92/192), Amsterdam.
- Royen, A.H.v. (1957). Artificial Aging at 100 °C Compared with Natural Aging at Room Temperature. *Association Technique de l'Industrie Papetière Bulletin* 6, p. 223-226.
- Royen, A.H.H.v. (1958). Vergelijking van de versnelde veroudering bij kamertemperatuur. *De Papierwereld* 12(9), p. 219-222,225.
- Schaeffer, T.T., Baker, M.T., Blyth-Hill, V., Reyden, D.v.d. (1992). Effects of Aqueous Light Bleaching on the Subsequent Aging of Paper. *Journal of the American Institute for Conservation* 31, p. 289-311.
- Sclawy, A.C. (1981). The Effects of Varying Relative Humidity Conditions on the Folding Endurance of Aged Paper Samples. In (Williams, J.C., ed.): *Preservation of Paper and Textiles of Historic and Artistic Interest. II*. American Chemical Society (Advances in Chemistry Series 193), Washington DC, p. 217-222.
- Shahani, C.J., Hengemihle, F.H., Weberg, N. (1989). The Effect of Variations in Relative Humidity on the Accelerated Aging of Paper. In (Zeronian, S.H., Needles, H.L., eds.): *Historic Textile and Paper Materials. II. Conservation and Characterization*. American Chemical Society (ACS Symposium Series 410), Washington DC, p. 63-80.

- Shahani, C.J. (1991). *Effects of Fluctuations in Relative Humidity and Temperature on Conditions within the Book Structure*. Paper at International Seminar on Research in Preservation and Conservation, New York.
- Shahani, C.J., Hengemihle, F.H., Weberg, N. (1993). The Effect of Fluctuations in Relative Humidity on Library and Archival Materials and their Aging within Contained Microenvironments. In: *Proceedings of the Pan-African Conference on Preservation and Conservation of Library and Archival Materials. Nairobi, Kenya, 21-25 June, 1993*. IFLA (ALP/PAC/RSCA), p. 61-70.
- Shahani, C.J. (1994). Accelerated Aging of Paper: Can It Really Foretell the Permanence of Paper? In: *Proceedings of the Workshop on the Effects of Aging on Printing and Writing Papers*. ASTM Institute for Standards Research, Philadelphia, p. 120-139.
- Skall, E. (1974). Alterungstests. *IADA Mitteilungen* 4(1), p. 37-46.
- Smith, R.D. (1970). New Approaches to Preservation. *The Library Quarterly* 40(1), p. 139-171 / In (Winger, H.W., Smith, R.D., eds.): *Deterioration and Preservation of Library Materials, The Thirty-fourth Annual Conference of the Graduate Library School, August 4-6, 1969*. The University of Chicago Press, Chicago, p. 139-175.
- Smith, R.D. (1972). A Comparison of Paper in Identical Copies of Books from the Lawrence University, the Newberry, and the New York Public Libraries. *Restaurator*, Supplement 2.
- Stamm, A.J. (1956). Thermal Degradation of Wood and Cellulose. *Industrial and Engineering Chemistry* 48(3), p. 413-417.
- Ströfer-Hua, E. (1990). Experimental Measurement: Interpreting, Extrapolation and Prediction by Accelerated Aging. *Restaurator* 11(4), p. 254-266.
- Tang, L.C., Jones, N.M.M. (1979). The Effects of Wash Water Quality on the Aging Characteristics of Paper. *Journal of the American Institute for Conservation* 18, p. 61-81.
- TAPPI (1963). *Relative Stability of Paper (by Effect of Heat on Folding Endurance)*. Technical Association of the Pulp & Paper Industry (TAPPI-T453-ts63; 72 hours at 105±2 °C).
- TAPPI (1985a). *Effect of Dry Heat on Properties of Paper*. Technical Association of the Pulp & Paper Industry (TAPPI-T453-pm85).
- TAPPI (1985b). *Effect of Moist Heat on Properties of Paper and Board*. Technical Association of the Pulp & Paper Industry (TAPPI-T544-pm85; 90 °C en 25% RH).
- Vitale, T., Erhardt, D. (1993). Changes in Paper Color due to Artificial Aging and the Effects of Washing on Color Removal. In (Bridgland, J., ed.): *Preprints. 10th Triennial Meeting, Washington DC, USA, 22-27 August 1993*. ICOM Committee for Conservation, Paris, p. 507-515.
- Wilson, W.K., Harvey, J.L., Mandel, J., Workman, T. (1955). Accelerated Aging of Record Papers Compared with Normal Aging. *Tappi* 38(9), p. 543-548.
- Wilson, W.K., Parks, E.J. (1971). *The National Bureau of Standards Research Program on Stability of Records*. Savannah.
- Wilson, W.K., Parks, E.J. (1980). Comparison of Accelerated Aging of Book Papers in 1937 with 36 Years Natural Aging. *Restaurator* 4, p. 1-55.

- Wilson, W.K., Parks, E.J. (1983). Historical Survey of Research at the National Bureau of Standards on Materials for Archival Records. *Restaurator* 5, p. 191-241.
- Wink, W.A., Ward, K., Swenson, H.A. (1968). Improving the Thermal Stability of Paper by Chemical Treatment. *Tappi* 51(10), p. 445-449.
- Wypych, J. (1990). *Weathering Handbook*. Chemtec Publishing, Toronto, p. 197-221.
- Yabrova, R.R. (1958a). Artificially Accelerated Aging of Paper. (USSR State Library im V.I. Lenin, Department for Book Preservation and Restoration, Moskou). In (Belyakova, L.A., Kozulina, O.V., eds.): *Collection of Materials on the Preservation of Library Resources. No. 3*. Translation: Israel Program for Scientific Translations Ltd. (IPST Catalogus 1022-3), Jerusalem, 1964. Oldbourne Press, London, p. 73-82.
- Yabrova, R.R. (1958b). The Effectiveness of Book Reinforcement by Poly-methylacrylate Emulsion. (USSR State Library im V.I. Lenin, Department for Book Preservation and Restoration, Moskou). In (Belyakova, L.A., Kozulina, O.V., eds.): *Collection of Materials on the Preservation of Library Resources. No. 3*. Translation: Israel Program for Scientific Translations Ltd. (IPST Catalogus 1022-3), Jerusalem, 1964. Oldbourne Press, London, p. 83-98.
- Zou, X., Uesaka, T., Gurnagul, N. (1996). Prediction of Paper Permanence by Accelerated Aging. I. Kinetic Analysis of the Aging Process. *Cellulose* 3, p. 243-267.

*Publications of the
European Commission on Preservation and Access*

*European Register of Microform Masters. Supporting International
Cooperation*

Werner Schwartz
1995, 10 pp.

Mass Deacidification. An Update of Possibilities and Limitations

Henk J. Porck
1996, 54 pp., ISBN 90-6984-162-2.

*Perservation Challenges in a Changing Political Climate. A Report
from Russia*

Galina Kislovskaya
1996, 20 pp. ISBN 90-6984-167-3

*Choosing to Preserve. Towards a cooperative strategy for long-term
access to the intellectual heritage*

Papers of the international conference organized by the European
Commission on Preservation and Access and Die Deutsche
Bibliothek, Leipzig/Frankfurt am Main, March 29-30, 1996
1997, vii + 165 pp. ISBN 90-6984-166-5

Digitisation as a Method of Preservation?

Final report of a working group of the Deutsche
Forschungsgemeinschaft (German Research Association)
Hartmut Weber & Marianne Dörr
1997, 27 pp. ISBN 90-6984-190-8

Digitizing Historical Pictorial Collections for the Internet

Stephen E. Ostrow
1998, vi + 28 pp. ISBN 90-6984-221-1

Selecting Research Collections for Digitization

Dan Hazen, Jeffrey Horrell, Jan Merrill-Oldham
1998, ix + 19 pp. ISBN 90-6984-242-4

Computerization of the Archivo General de Indias: Strategies and Results

Pedro González
1999, vi + 57 pp. ISBN 90-6984-241-6

*Avoiding Technological Quicksand. Finding a Viable Technical
Foundation for Digital Preservation*

Jeff Rothenberg
1999, vii + 35 pp. ISBN 90-6984-257-2

Weten Geweten Gewist. Bedreigde wetenschappelijke collecties in archieven en bibliotheken

Gabriëlle Beentjes, Mariska Herweijer, Yola de Lusenet, Karin Scheper and Paula Witkamp

1997, 45 pp. ISBN 90-6984-192-4

Publication in Dutch, written to accompany a small exhibition on the dangers threatening scientific collections in archives and libraries. The exhibition was first shown in the building of the Royal Netherlands Academy of Arts and Sciences, where the ECPA is housed.

In the Picture

Preservation and digitisation of European photographic collections

Edwin Klijn, Yola de Lusenet

2000, vi + 69 pp. ISBN 90-6984-294-7

Rate of paper degradation: The predictive value of artificial aging tests. Amsterdam: European Commission on Preservation and Access. ^ Bansa, H. (1992).Â A comparison of artificial ageing with 27 years of natural ageing. 2008 AICCM Book, Paper and Photographic Materials Symposium, 81-89. ^ [2], Library of Congress (2008). What is the importance of predicting Conversion Rates? You may have asked yourself whatâ€™s the best channel to advertise a product or what will be the impact of a digital campaign, or even wonder if you will get your advertising money back throughout product sales. Trust me, we all have been there, so in this post I will show you the key factors and the importance of predicting conversion rates using Naive Bayes and Logistic Regression. Choosing the correct advertisement directly impacts the revenue of the e-commerce sites and user satisfaction. For long run advertising campaigns it can be ver Rate of paper degradation : the predictive value of artificial aging tests / Henk J. Porck. Porck, Henk J. Date. 2000. Where to find it. Access this item on the Wellcome Library website. About this work. PDF | Paper aging and conservation are matters of concern to those responsible for archives and library collections. Wood-derived fibers are mainly | Find, read and cite all the research you need on ResearchGate.Â ed aging of papers of pure cellulose with low initial pH and degree of polymerization. results in embrittlement, with a significant loss of paper strength. This effect is mainly the.Â This mechanism is relevant in the study of the rate of degradation of. oxidised cellulose in alkaline medium, i.e., after deacidification. In this case, the overall. View Paper Degradation Research Papers on Academia.edu for free.Â The traditional Oddy test assesses the impact of material off-gassing on collection items through the corrosion of metal coupons, a result that does not necessarily correlate well to the Library's primarily paper-based collections. Dr. Eric Breitung discusses research in the Preservation Research and Testing Division that uses paper instead of metal as a sensor and multiple analytical methods to assess the degradation level of the paper sensor.Â The SurveNIR system is able to determine and to rate the condition of paper in collections in a scientific manner regarding its degree of degradation and hazard. The SurveNIR system is based on statistical evaluation of near infrared more.